

Technical Information






RAX0700

RAXON UC30 UNIVERSAL

ANTISCRATCH CLEAR

- ◆ High solids content, excellent weathering resistance
- ◆ Good polishing behaviour
- ◆ High gloss, high finish quality

Application

	Mixing Ratio	100 % by volume	RAX0700
		50 % by volume	RAX0678
	2:1+10 %	10 % by volume	THINNER
	Spray viscosity at 20°C	DIN 4: 18-20 s	
	Potlife at 20°C	4 h	
	HVLP spray gun		
	Nozzle size	1.3 mm	
	Application pressure	2 bar	
	Nozzle pressure	0.7 bar	
	Compliant gravity-feed spray gun		
	Nozzle Size	1.3-1.4 mm	
	Application Pressure	2 bar	
	Number of spray coats	2	
	Film thickness	50-70 µm	
	Flash off at 20°C	2-3 min after each spray coat	

Safety advice:

The products are suitable for professional use only.
It cannot be ruled out that this product contains particles < 0.1 µm.



Technical Information

RAX0700

RAXON UC30 UNIVERSAL

ANTISCRATCH CLEAR

Drying

	Drying at 20°C	8 h
	Drying at 60°C	30 min
	Infrared (short wave)	8 min
	Infrared (medium wave)	10-15 min

Please note: For automotive refinish, repair instructions of vehicle manufacturers, in particular regarding installed sensor technology, must always be observed in addition to the processing instructions given within this document.

Safety advice:

The products are suitable for professional use only.

It cannot be ruled out that this product contains particles < 0.1 µm.